



**ED FAGAN INC.**

# EFI Alloy 79

# Soft Magnetic Alloys

769 Susquehanna Avenue, Franklin Lakes, NJ 07417 • **phone 201.891.4003**  
10537 Humbolt Street, Los Alamitos, CA 90720 • **phone 562.431.2568**

## DESCRIPTION


A soft magnetic alloy consisting of 80% Nickel, 5% Molybdenum, and balance Iron used where extremely high initial & maximum permeability and minimum hysteresis is needed.

## APPLICATIONS

Electro-magnetic shielding, specialty transformer laminations, toroidal tape wound cores, high quality motor laminations, stepping motors.

AKA: Magnifer 7904<sup>2</sup>, Carpenter HyMu 80<sup>1</sup>, Hipernom<sup>1</sup>, Moly-Permalloy, Permalloy 80

Footnotes: 1. Trademark Carpenter Technology Corp., Reading PA;  
2. Trademark ThyssenKrupp-VDM, Germany



## TYPICAL DC MAGNETIC PROPERTIES

<b>Saturation Induction - Gausses</b>	8,700
<b>Maximum Permeability</b>	230,000
<b>Coercive Force - Oersteds</b>	0.015
<b>Coercive Force - A/m</b>	1.19

## TYPICAL AC MAGNETIC PROPERTIES

<b>Core Loss W/lb @ 400Hz &amp; 20k G</b>	N/A
<b>B-40 Permeability @ 60Hz</b>	45,000

N/A = not a typical application value

## PHYSICAL PROPERTIES

<b>Density</b>	<b>lb/cu in</b>	0.316
<b>Specific Gravity</b>		8.74
<b>Curie Temp</b>	<b>°F</b>	860
	<b>°C</b>	460
<b>Melting Point</b>	<b>°F</b>	2650
	<b>°C</b>	1454
<b>Electrical Resistivity</b>	<b>micro-ohm-cm</b>	59
	<b>ohm-cir mil/ft</b>	394
<b>Thermal Conductivity</b>	<b>W/cm °C</b>	0.35
	<b>BTU-in/sq. ft-hr-°F</b>	240
<b>Specific Heat</b>	<b>Cal/g- °C</b>	-
	<b>BTU/lbm-°F</b>	-
<b>Thermal Expansion</b>	<b>ppm/°F(75°F to 842°F)</b>	7.5
	<b>ppm/°C(25°C to 450°C)</b>	13.6

## MECHANICAL PROPERTIES

<b>Tensile Strength</b>	<b>ksi</b>	98
	<b>MPa</b>	676
<b>Yield Strength</b>	<b>ksi</b>	38
	<b>MPa</b>	262
<b>Elongation</b>	<b>% in 2 in.</b>	40
<b>Typical Hardness</b>	<b>Rockwell</b>	HRB 85
<b>Modulus of Elasticity</b>	<b>Mpsi</b>	31.4
	<b>kMPa</b>	217

## FORMS AVAILABLE

<b>Rod</b>	0.500" - 1.5"	<b>Coil</b>	0.040" - 0.025"
<b>Sheet*</b>	0.010" - 0.062"	<b>Sq. Bar</b>	1.812"

\*Though not a standard stock item, we may be able to supply you with the exact size, shape & quantities you require. Please call.

## SPECIFICATIONS

**ASTM A753, MIL N-1441C, AMS N-1441C**

## CHEMISTRY - maximum % unless noted

<b>Iron</b>	Bal.	<b>Silicon</b>	0.42
<b>Nominal Nickel</b>	80	<b>Vanadium</b>	-
<b>Nominal Cobalt</b>	-	<b>Niobium</b>	-
<b>Molybdenum</b>	5.0	<b>Phosphorus</b>	0.02
<b>Carbon</b>	0.03	<b>Sulfur</b>	0.008
<b>Manganese</b>	0.95		



Ed Fagan Inc also specializes in locating exotic materials. So, if you can't locate that hard-to-find material you need... Put EFI's material locator service to work for you!

[www.Material-locator.com](http://www.Material-locator.com)

**THE MATERIALS YOU NEED,  
WHEN YOU NEED THEM**



toll free 800.348.6268  
[www.edfagan.com](http://www.edfagan.com)  
[sales@edfagan.com](mailto:sales@edfagan.com)  
international sales  
+44 (0) 1548 858 770

**efi**  
ED FAGAN INC.

## Glass Sealing/ Controlled Expansion Alloys

EFI provides the highest quality materials including materials from Carpenter Technology Corp.

### ASTM F15 Alloy:

aka Kovar & Pernifer 2918  
Coil/Strip, Sheet, Plate,  
Bar, Wire

### Invar 36:

Bar, Sheet, Plate

### 42/46/48/52 Alloy:

Coil/Strip, Sheet, Plate, Bar

### Electronic Nickel

### 200/201/233/270:

Coil/Strip, Rod, Sheet, Plate

## Soft Magnetic Alloys/ EMI Shielding & Laminations

EFI is a distributor of magnetic shielding alloys for the world's leading producer of these alloys – ThyssenKrupp VDM.

### EFI Alloy 79:

aka Magnifer 7904,  
Moly-Permalloy & HyMu 80  
Sheet, Coil/Strip

### EFI 50:

aka Magnifer 50 & High Perm 49  
Bar, Coil/Strip

### Carpenter VimVar Core Iron:

Rod, Bar

### Carpenter Hipercro 50:

Coil/Strip, Billet

## Refractory Metals/Alloys

EFI is a stocking distributor of Molybdenum & Tungsten products, as well as many other refractory metals and alloys, providing the highest quality materials available.

### Molybdenum:

Bar, Sheet, Plate, Coil/Strip

### TZM Molybdenum Alloy:

Sheet, Bar

### Tungsten:

Bar, Coil/Strip, Sheet

**Tantalum:** Sheet, Tubing

**Niobium:** Strip

**Tungsten Alloy:** Rod, Shapes

## Hard-to-Find Special Purpose Metals, Alloys and Materials

Are you spending too much of your valuable time trying to locate suppliers of specialty metals and materials? Use EFI's Material Locator (see below) to source it for you so you can get back to doing what you do best.

- Coil/Strip
- Sheet
- Plate
- Rod
- Tube
- Pipe
- Wire

## JUST IN TIME DELIVERY

All standard stock items can be **shipped within 24 hours** – and are often **shipped the same day**. All materials are certified with shipment.

## METALS WE DISTRIBUTE

Titanium  
Zirconium

High Temperature Alloys  
Corrosion Resistant Alloys  
Stainless Steel

Copper – OFE, OFHC  
Brass & Bronze  
Beryllium Copper

## SERVICES WE OFFER

Slitting, Shearing, Saw Cutting, Centerless Grinding, Water-jet Cutting, Laser Cutting,  
Custom Stocking Programs • Consignment Programs



Ed Fagan Inc also specializes in locating exotic materials. So, if you can't locate that hard-to-find material you need... Put EFI's material locator service to work for you!

[www.Material-locator.com](http://www.Material-locator.com)

**THE MATERIALS YOU NEED,  
WHEN YOU NEED THEM**



toll free 800.348.6268  
[www.edfagan.com](http://www.edfagan.com)  
[sales@edfagan.com](mailto:sales@edfagan.com)  
international sales  
+44 (0) 1548 858 770

**efi**  
ED FAGAN INC.