



ED FAGAN INC.

EFI Alloy 50

Soft Magnetic Alloys

769 Susquehanna Avenue, Franklin Lakes, NJ 07417 • **phone 201.891.4003**
10537 Humbolt Street, Los Alamitos, CA 90720 • **phone 562.431.2568**

DESCRIPTION



A soft magnetic alloy, consisting of 49% Nickel, balance Iron used where high initial permeability, maximum permeability, and low core loss is needed.

APPLICATIONS

Transformer cores, highly efficient motors, shielding, and specialized electronic devices, such as LF power transducers, chokes, relay parts, solenoids & oscillators.

AKA: Magnifer 50¹, Carpenter High Permeability 49², Alloy 47-50

Footnotes: 1. Trademark VDM Metals GmbH, Germany; 2. Trademark Carpenter Technology Corp., Reading PA



TYPICAL DC MAGNETIC PROPERTIES

Saturation Induction - Gauss	14,500
Maximum Permeability	100,000
Coercive Force - Oersteds	0.06
Coercive Force - A/m	4.77

All magnetic testing was performed in accordance with applicable ASTM specification. Please refer to appropriate specification for details. Procedures are product specific.

TYPICAL AC MAGNETIC PROPERTIES

Core Loss W/lb @ 400Hz & 20k G	N/A
B-40 Permeability @ 60Hz	6,500

N/A = not a typical application value

PHYSICAL PROPERTIES

Density	lb/cu in	0.295
Specific Gravity		8.18
Curie Temp	°F	840
	°C	450
Melting Point	°F	2600
	°C	1427
Electrical Resistivity	micro-ohm-cm	49
	ohm-cir mil/ft	290
Thermal Conductivity	W/cm °C	0.13
	BTU-in/sq. ft-hr-°F	90
Specific Heat	Cal/g-°C	0.12
	BTU/lbm-°F	0.12
Thermal Expansion	ppm/°F(75°F to 842°F)	5.0
	ppm/°C(25°C to 450°C)	9.0

MECHANICAL PROPERTIES

Tensile Strength	ksi	75
	MPa	518
Yield Strength	ksi	23
	MPa	159
Elongation	% in 2 in.	40
Typical Hardness	Rockwell	HRB 80
Modulus of Elasticity	Mpsi	24
	kMPa	166

FORMS AVAILABLE

Rod	0.140" - 4.0"	Coil	0.004" - 0.062"
Sq. Bar	1.030" - 2.030"		

If you do not see the size or form you require listed above, please call us. We add new stock material frequently, and may have the size and form you need.

SPECIFICATIONS

ASTM A753 Type 2, **MIL** N-14411C Comp 3

CHEMISTRY - maximum % unless noted

Iron	Bal.	Silicon	0.50
Nominal Nickel	49	Vanadium	-
Nominal Cobalt	0.50	Niobium	-
Molybdenum	0.30	Phosphorus	0.03
Carbon	0.05	Sulfur	0.01
Manganese	0.80	Chromium	0.30



Ed Fagan Inc also specializes in locating exotic materials. So, if you can't locate that hard-to-find material you need... Put EFI's material locator service to work for you!

www.material-locator.com

THE MATERIALS YOU NEED, WHEN YOU NEED THEM



toll free 800.348.6268

www.edfagan.com

sales@edfagan.com

international sales

+44 (0) 1548 858 770



ED FAGAN INC.

11/2016

Glass Sealing / Controlled Expansion Alloys / Electrical & Electronic Nickel

EFI provides the highest quality materials including materials from Carpenter Technology Corp.

ASTM F15 Alloy:

aka Kovar, Pernifer 2918, NILO K & Dilvar P1

Coil/Strip, Sheet, Plate, Round Bar

Invar 36:

aka Pernifer 36, NILO 36 & Invar Steel

Round Bar, Sheet, Plate

Super Invar 32-5:

Round bar, Sheet, Plate

42/*46/48/52 Alloy:

aka Pernifer 40, 46, 48 & 50;

NILO 42, 46, 48 & 50;

Glass Seal 42, 46, 48 & 50

Coil/Strip, Sheet, Plate, Round Bar

Electronic Nickel

200/201/233/270:

Coil/Strip, Round Bar, Sheet

**Products listed in Italics are special order and not standard stock items. Please call for availability.*

Soft Magnetic Alloys/ EMI Shielding & Laminations

EFI is a distributor of magnetic shielding alloys for the world's leading producer of these alloys – VDM Metals GmbH.

EFI Alloy 79:

aka Magnifer 7904, Moly-Permalloy,

HyMu 80, Hypernom & Permalloy 80

Round Bar, Sheet, Coil/Strip

EFI Alloy 50:

aka Magnifer 50, High Permeability 49 & Alloy 47-50

Round & Square Bar, Coil/Strip

Carpenter VimVar Core Iron:

Round Bar

Carpenter Hiperco 50:

Plate, Coil/Strip

Carpenter Hiperco 50A:

Round Bar

Radiometal 4550:

Round Bar, Coil/Strip

Refractory Metals/Alloys

EFI is a stocking distributor of Molybdenum & Tungsten products, as well as many other refractory metals and alloys, providing the highest quality materials available.

Molybdenum:

Round Bar, Sheet, Plate,

Threaded Rod & Nuts

**Foil/Coil/Strip, Wire*

TZM Molybdenum Alloy:

Round Bar, Sheet, Plate

Tungsten:

Round Bar, Plate, **Sheet, *Wire*

Tungsten Alloy:

Round Bar, **Sheet, *Plate,*

**Shapes, *Flat Blanks*

**Tantalum: Round Bar, Sheet*

**Niobium: Foil/Coil/Strip*

**Rhenium: Sheet*

**Products listed in Italics are special order and not standard stock items. Please call for availability.*

METALS WE DISTRIBUTE

Titanium - CP & 6Al-4V • High Temperature Alloys • Corrosion Resistant Alloys • Stainless Steel

JUST IN TIME DELIVERY: All **standard stock** items can be **shipped within 24 hours** – and are often **shipped the same day**. For **special order** materials, EFI has long relationships with the manufacturers of these materials, so please contact a sales rep to discuss price and delivery options. All materials can be certified with shipment.

SERVICES WE OFFER

Slitting, Shearing, Saw Cutting, Centerless Grinding, Water-jet Cutting, Laser Cutting, Custom Stocking Programs, Consignment Programs



Are you spending too much of your valuable time trying to locate specialty metals and materials? If you can't locate the hard-to-find materials you need, use EFI's Material Locator to source them for you.

www.material-locator.com

**THE MATERIALS YOU NEED,
WHEN YOU NEED THEM**



toll free 800.348.6268
www.edfagan.com
sales@edfagan.com
international sales
+44 (0) 1548 858 770

efi
ED FAGAN INC.