



26
Fe
55.845
Iron
28
Ni
58.6934
Nickel

Alloy 48

Controlled Expansion Alloys

DESCRIPTION

A controlled expansion alloy consisting of approximately 48% Nickel and the balance Iron. This binary nickel-iron alloy is applicable to a wide variety of electronic applications that require a low coefficient of expansion at 400°C for glass-to-metal seals in soft lead or soda lime glasses. Alloy 48 is also referenced under the manufacturer's trademark names of Pernifer®48 and NILO® 48.

APPLICATIONS

Glass-to-metal seals for electronic tubes and hermetic devices.

TYPICAL PHYSICAL PROPERTIES

Density	lb/cu in	0.298
Specific Gravity		8.25
Curie Temp	°F	880
	°C	471
Melting Point	°F	2640
	°C	1450
Electrical Resistivity	ohm-cir mil/ft - (68°F)	283
	Microhms-cm - (20°C)	47
Thermal Conductivity	BTU-in/sq.ft-hr - (68°F)	116
	W/m °C - (20°C)	16.7

Source: ASTM F30-96 (2017) | Special Metals Corp. Nilo 48 Data v. 9/04

FORMS | SIZES AVAILABLE

Round Bar Rod	0.062" - 4.000"
-----------------	-----------------

Listed above are our standard stock items. Our inventory fluctuates based on market demands. If you do not see the size or form you require, please call us.

TYPICAL MECHANICAL PROPERTIES

Tensile Strength	ksi (MPa)	75 (520)
Yield Strength	ksi (MPa)	38 (260)
Elongation	% in 2 in.	43
Hardness Annealed	Rockwell HRB max.	80
Modulus of Elasticity	ksi (GPa)	23.2 (160)

Hot-rolled, annealed bar.
Source: ASTM F30-96 (2017) | Special Metals Corp Nilo 48 Data v. 9/04

AVERAGE LINEAR COEFFICIENT OF THERMAL EXPANSION $\mu\text{m/m}\cdot\text{°C}^*$

Temperature Range °C	48 Alloy UNS K94800
30 to 300	8.8
30 to 400*	8.2 to 9.2*
30 to 500	9.4
30 to 550*	9.6 to 10.3*
30 to 600	10.4
30 to 700	11.3
30 to 800	12.1
30 to 900	13.0
30 to 1000	13.9

Source: ASTM F30 - 96 (2017), Table X1.1, 48 Alloy; *ASTM F30-96 Table 2 Range

CHEMISTRY %

Nickel 48 nom., Manganese 0.80 max., Silicon 0.30 max., Carbon 0.05 max., Chromium 0.25 max., Phosphorus 0.025 max., Sulfur 0.025 max., Aluminum 0.10 max., Bal. Iron. Cobalt is present as an incidental element and shall be reported separately. Source: ASTM F30-96 (2017), Table 1, 48 Alloy

SPECIFICATIONS

ASTM F30 • AMS I-23011 CL 3 • MIL-I-23011 CL 3 • UNS K94800



Special Purpose Alloys & Metals From Stock

Controlled Expansion | Glass Sealing

Ed Fagan Inc. supplies the highest quality metals and alloys including materials from Carpenter Technology Corp.

Kovar® | ASTM F15 Alloy

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil
Trade Names: Kovar®, Pernifer® 2918, NILO K®, DilverP1®

Alloy 42/46/48/52

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil
Trade Names: Pernifer®40, 46, 48, 50; NILO® 42, 46, 48, 50;
Glass Sealing 42, 46, 48, 52

Free-Cut Invar "36"® Alloy

Forms: Round Bar/Rod

Invar "36"® Alloy

Forms: Plate, Sheet
Trade Names: Pernifer® 36, NILO® 36, Invar

Super Invar 32-5®

Forms: Plate, Round Bar/Rod, Sheet

Refractory Metals and Alloys

Ed Fagan Inc. is your leading source for quality refractory metals & alloys. We stock DFARS Molybdenum, ML/MLS/MLR, Molybdenum TZM, Tantalum & Tungsten manufactured from Plansee.

Molybdenum

Forms: Plate, Round Bar/Rod, Sheet/Coiled Sheet, Threaded Rod/Nuts, Wire

Molybdenum Lanthanum Oxide (ML)

Forms: Sheet – Stress Relieved, Recrystallized

Molybdenum TZM

Forms: Plate, Round Bar/Rod, Sheet

Niobium

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil, Wire

Rhenium

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil

Tantalum

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil, Wire

Tungsten

Forms: Plate, Precision Cut Wire, Round Bar/Rod, Sheet

Tungsten Alloys

Forms: Blanks, Flats, Parts, Plate/Sheet, Rod, Shapes

Soft Magnetic Alloys | EMI Shielding & Laminations

Ed Fagan Inc. is a distributor of "EMI shielding alloys" for VDM Metals GmbH the world's leading producer of these alloys.

EFI Alloy 50

Forms: Round Bar/Rod, Square Bar, Strip/Coil, Wire Rod
Trade Names: High Permeability 49®, Magnifer® 50

EFI Alloy 79

Forms: Rectangular Bar, Round Bar/Rod, Sheet, Strip/Coil
Trade Names: Hipernom, HyMu80®, Magnifer® 7904, Molypermalloy, Permalloy 80®

Hiperco® 50

Forms: Strip/Coil

Hiperco® 50A

Forms: Plate, Round Bar/Rod, Strip/Coil

Hiperco® 50 HS

Forms: Strip/Coil

Carpenter VimVar Core Iron

Forms: Round Bar/Rod

Electrical & Electronic Nickels

Ed Fagan Inc. supplies select, commercially pure grades of Nickel in various forms and sizes.

Electronic Nickels

200/201/205/233/270

Forms: Round Bar/Rod, Sheet, Strip/Coil, Wire

Alloys and Metals We Distribute

Corrosion Resistant Alloys • High-Temperature Alloys • Stainless Steel
• Titanium – CP, 6 Al-4V

Ed Fagan Inc. Services

Slitting, Shearing, Saw Cutting, Grinding, Water Jet Cutting, Laser Cutting,
Custom Stocking and Consignment Programs

JUST-IN-TIME DELIVERY: All of our **standard stock** items can be **shipped within 24-hours** of your order confirmation and most are **shipped the same day**. All materials certified with shipment. For special orders and non-stock materials, contact our sales team for our competitive pricing and delivery lead times.